



## COMMERCIAL GRADE CELL CAST ACRYLIC

### TYPICAL PHYSICAL PROPERTIES

	Units	Value: 3mm	Test Method
Specific Gravity	-	1.19	D 792
Water Absorbtion	(%)	0.3 – 0.4	D 570

### MECHANICAL

Impact Strength, Izod	kgf . cm/cm	2.2	D 256-
Charpy Impact Strength	kgf . cm/cm <sup>2</sup>	3.0	D 256
Tensile Strength	kgf/cm <sup>2</sup>	780	D 638
Tensile Modulus	kgf/cm <sup>2</sup>	3.3 x 10 <sup>4</sup>	D 638
Flexural Strength	kgf/cm <sup>2</sup>	1200	D 790
Flexural Modulus	kgf/cm <sup>2</sup>	3.3 x 10 <sup>4</sup>	D 790
Rockwell Hardness	-	M-100	D 785

### THERMAL

Thermal Conductivity	cal/cm . sec . °C	5 x 10 <sup>-4</sup>	-
Coefficient of linear expansion	cm/cm . °C	7 – 8 x 10 <sup>-5</sup>	D 696
Heat Distortion Temperature	°C	100	D 648
Vicat Softening Point	°C	118	D 1525

### ELECTRICAL

Dielectric Strength	kV/mm	18	D 149
---------------------	-------	----	-------

### OPTICAL PROPERTIES

Light Transmission Clear Sheet (000)	%	93	-
Light Transmission Sign Grade Opal Sheet (445)	%	50	-
Light Transmission Skylight Grade Opal Sheet (010)	%	70	-

This information is intended as a guideline for designers and processors of thermoplastics. Because design and processing is complex, a set solution will not solve all problems. Observation on a "trial and error" basis may be required to achieve desired results.

No information supplied by Industrial Plastic Solutions constitutes a warranty regarding product performance or use. Any information regarding performance or use is only offered as suggestion for investigation for use. Industrial Plastic Solutions offers no warranties, expressed or implied, concerning the suitability or fitness of any of its products for any particular purpose. It is the responsibility of the customer to determine that the product is safe, lawful and technically suitable for the intended use.